

PRIMATOP® PPC 015-NB

PP

Amco Polymers

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|-------------------------------------|-------|---------|---------------|
| ASTM Data | | | |
| Melt Flow Index, MFI | 1.5 | g/10min | ASTM D 1238 |
| Temperature | 230 | °C | - |
| Load | 2.16 | kg | - |

| Mechanical properties | Value | Unit | Test Standard |
|-----------------------------|-------|------|---------------|
| ASTM Data | | | |
| Tensile Strength at Yield | 26.2 | MPa | ASTM D 638 |
| Izod Impact notched, 1/8 in | N | J/m | ASTM D 256 |

| Thermal properties | Value | Unit | Test Standard |
|--------------------|-------|------|---------------|
| ASTM Data | | | |
| DTUL @ 66 psi | 90.6 | °C | ASTM D 648 |

| Other properties | Value | Unit | Test Standard |
|--------------------------------------|-------|-------------------|---------------|
| Other Standards^[S] | | | |
| Density | 900 | kg/m ³ | ASTM D 1505 |

S: These properties are reported by the producer according standards that are different to our defaults.

Characteristics**Processing**

Sheet Extrusion, Blow Molding

Certifications

Food contact, Food approval FDA 21 CFR

Special Characteristics

High impact or impact modified

Regional Availability

North America

Features

Copolymer, Impact Copolymer