

PRIMATOP® PPC 250-20 NA

PP

Amco Polymers

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	25	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	26.9	MPa	ASTM D 638
Izod Impact notched, 1/8 in	107	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Other Standards^{S]}			
Density	900	kg/m ³	ASTM D 1505

S: These properties are reported by the producer according standards that are different to our defaults.

Characteristics**Processing**

Injection Molding

Additives

Release agent

Special Characteristics

Anti-static, High impact or impact modified

Features

Nucleated, Copolymer, Impact Copolymer

Certifications

Food contact, Food approval FDA 21 CFR

Regional Availability

North America