

PRIMATOP® PPC 350-20

PP

Amco Polymers

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	35	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	24.1	MPa	ASTM D 638
Elongation at Yield	6	%	ASTM D 638
Izod Impact notched, 1/8 in	107	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Other Standards^[S]			
Density	900	kg/m ³	ASTM D 1505

S: These properties are reported by the producer according standards that are different to our defaults.

Characteristics**Processing**

Injection Molding

Features

Copolymer, Impact Copolymer

Additives

Release agent

Certifications

Food contact, Food approval FDA 21 CFR

Special Characteristics

High impact or impact modified

Regional Availability

North America