

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|-------------------------------------|-------|-------------------|---------------|
| ASTM Data | | | |
| Melt Flow Index, MFI | 14 | g/10min | ASTM D 1238 |
| Temperature | 230 | °C | - |
| Load | 2.16 | kg | - |
| Mechanical properties | | | |
| ASTM Data | | | |
| Tensile Strength at Yield | 32 | MPa | ASTM D 638 |
| Elongation at Yield | 13 | % | ASTM D 638 |
| Izod Impact notched, 1/8 in | 37 | J/m | ASTM D 256 |
| Thermal properties | | | |
| ASTM Data | | | |
| DTUL @ 66 psi | 96 | °C | ASTM D 648 |
| Other properties | | | |
| Density | 900 | kg/m ³ | ASTM D 792 |

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Features

Homopolymer

Chemical Resistance

General Chemical Resistance, Environmental Stress Crack Resistance

Applications

Packaging

Regional Availability

North America