

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	1.4	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	28	MPa	ASTM D 638
Elongation at Yield	11	%	ASTM D 638
Izod Impact notched, 1/8 in	144	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	82	°C	ASTM D 648
Other properties			
Density	900	kg/m ³	ASTM D 792

Characteristics

Processing

Blown Film Extrusion, Pipe/Tube Extrusion, Profile Extrusion, Sheet Extrusion, Other Extrusion, Thermoforming

Delivery form

Pellets

Special Characteristics

High impact or impact modified, Heat stabilized or stable to heat

Features

Copolymer, Impact Copolymer

Applications

Automotive, Packaging

Regional Availability

North America