

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	4	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Yield stress	21	MPa	ISO 527
Yield strain	9	%	ISO 527
Flexural modulus, 23°C	970	MPa	ISO 178
Charpy notched impact strength, +23°C	18	kJ/m ²	ISO 179/1eA
ASTM Data			
Tensile Strength at Yield	21	MPa	ASTM D 638
Elongation at Yield	8	%	ASTM D 638
Izod Impact notched, 1/8 in	N	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	74	°C	ASTM D 648
Other properties			
Density	900	kg/m ³	ISO 1183
Density	900	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding, Profile Extrusion, Sheet Extrusion, Other Extrusion

Delivery form

Pellets

Special Characteristics

High impact or impact modified

Features

Copolymer, Impact Copolymer

Applications

Automotive

Regional Availability

North America