

Pro-fax EP315J

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	2.6	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	22	MPa	ASTM D 638
Elongation at Yield	7	%	ASTM D 638
Electrical properties			
ASTM Data			
Dissipation Factor, 1 MHz	0.0003	-	ASTM D 150
Volume Resistivity	>1E15	Ohm*cm	ASTM D 257
Other properties			
Density	900	kg/m ³	ASTM D 792

Characteristics**Features**

Copolymer, Impact Copolymer

Applications

Electrical and Electronical

Chemical Resistance

Environmental Stress Crack Resistance

Regional Availability

North America