

Pro-fax EP349U

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	80	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	21	MPa	ASTM D 638
Elongation at Yield	5	%	ASTM D 638
Izod Impact notched, 1/8 in	117	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	100	°C	ASTM D 648
Other properties			
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Delivery form

Pellets

Special Characteristics

Anti-static, High impact or impact modified

Features

Nucleated, Copolymer, Impact Copolymer

Certifications

Food contact

Applications

Packaging, Sports Equipment

Regional Availability

North America