

Pro-fax EP545U

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	80	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	24	MPa	ASTM D 638
Elongation at Yield	4	%	ASTM D 638
Izod Impact notched, 1/8 in	91	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	108	°C	ASTM D 648
Other properties			
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Delivery form

Pellets

Special Characteristics

Anti-static

Features

Nucleated, Copolymer, Impact Copolymer

Certifications

Food contact

Applications

Packaging

Regional Availability

North America