

Pro-fax EP713H

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	1.8	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	30	MPa	ASTM D 638
Elongation at Yield	7	%	ASTM D 638
Izod Impact notched, 1/8 in	294	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	106	°C	ASTM D 648
Other properties			
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Profile Extrusion, Sheet Extrusion, Blow Molding, Thermoforming

Delivery form

Pellets

Special Characteristics

High impact or impact modified

Features

Nucleated, Copolymer, Impact Copolymer

Certifications

Food contact

Applications

Packaging

Regional Availability

North America