

Pro-fax RP311H

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	2	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	28	MPa	ASTM D 638
Elongation at Yield	13	%	ASTM D 638
Izod Impact notched, 1/8 in	215	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	80	°C	ASTM D 648
Optical properties			
ASTM Data			
Haze	25	%	ASTM D 1003
Other properties			
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Sheet Extrusion, Blow Molding, Thermoforming

Delivery form

Pellets

Special Characteristics

Anti-static

Features

Nucleated, Copolymer, Random Copolymer

Applications

Packaging

Regional Availability

North America