

Pro-fax RP320N

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	12	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	28	MPa	ASTM D 638
Elongation at Yield	13	%	ASTM D 638
Izod Impact notched, 1/8 in	48	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	77	°C	ASTM D 648
Other properties			
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Film Extrusion

Delivery form

Pellets

Special Characteristics

High impact or impact modified

Features

Foamable, Heat Sealable, Copolymer, Random Copolymer

Certifications

Food contact

Applications

Building Construction, Packaging

Regional Availability

North America