

**Pro-fax SC204**

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>4</b>	g/10min	ASTM D 1238
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>33</b>	MPa	ASTM D 638
Elongation at Yield	<b>8</b>	%	ASTM D 638
Izod Impact notched, 1/8 in	<b>96</b>	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
DTUL @ 66 psi	<b>113</b>	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	<b>900</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Sheet Extrusion, Thermoforming

**Features**

Nucleated, Copolymer, Impact Copolymer

**Delivery form**

Pellets

**Applications**

Packaging

**Special Characteristics**

Anti-static, High impact or impact modified

**Regional Availability**

North America