

**Pro-fax SR549M**

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	11	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength at Yield	30	MPa	ASTM D 638
Elongation at Yield	12	%	ASTM D 638
Izod Impact notched, 1/8 in	64	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
DTUL @ 66 psi	77	°C	ASTM D 648
<b>Optical properties</b>			
<b>ASTM Data</b>			
Haze	7	%	ASTM D 1003
<b>Other properties</b>			
Density	900	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding, Blow Molding

**Delivery form**

Pellets

**Special Characteristics**

Anti-static, High impact or impact modified

**Features**

Copolymer, Random Copolymer

**Applications**

Packaging

**Regional Availability**

North America