

Pro-fax SV258

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	1.2	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	28	MPa	ASTM D 638
Elongation at Yield	11	%	ASTM D 638
Izod Impact notched, 1/8 in	208	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	82	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Profile Extrusion, Sheet Extrusion, Blow Molding, Thermoforming

Delivery form

Pellets

Special Characteristics

High impact or impact modified

Features

Copolymer, Impact Copolymer

Applications

Automotive, Packaging

Regional Availability

North America