

**Profax™ PL734**

PP

Indelpro S.A. de C.V.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	22	g/10min	ASTM D 1238

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength at Yield	31	MPa	ASTM D 638
Elongation at Yield	11	%	ASTM D 638
Flexural Modulus	1150	MPa	ASTM D 790
Izod Impact notched, 1/8 in	32	J/m	ASTM D 256

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	900	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Special Characteristics**

Heat stabilized or stable to heat

**Features**

Homopolymer

**Certifications**

Food contact, Food approval FDA 21 CFR

**Applications**

Automotive

**Regional Availability**

South and Central America