

Profax™ PL874

PP

Indelpro S.A. de C.V.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	34	g/10min	ASTM D 1238

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	35	MPa	ASTM D 638
Elongation at Yield	10.8	%	ASTM D 638
Flexural Modulus	1400	MPa	ASTM D 790
Izod Impact notched, 1/8 in	26.7	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	107	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Coating

Features

Homopolymer

Certifications

Food contact, Food approval FDA 21 CFR

Applications

Multifilament

Regional Availability

South and Central America