

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	6.5	g/10min	ASTM D 1238

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	30	MPa	ASTM D 638
Elongation at Yield	7.9	%	ASTM D 638
Flexural Modulus	1397	MPa	ASTM D 790
Izod Impact notched, 1/8 in	69.4	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding, Compression Molding

Special Characteristics

Anti-static

Features

Nucleated, Impact Copolymer

Certifications

Food contact, Food approval FDA 21 CFR

Regional Availability

South and Central America