

Profax™ SL146N

PP

Indelpro S.A. de C.V.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	0.3	g/10min	ASTM D 1238

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	25.8	MPa	ASTM D 638
Elongation at Yield	12.6	%	ASTM D 638
Flexural Modulus	768	MPa	ASTM D 790
Izod Impact notched, 1/8 in	551	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	133	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Other Extrusion

Special Characteristics

Heat stabilized or stable to heat

Features

Random Copolymer

Certifications

Food contact, Food approval FDA 21 CFR

Applications

Chemical Process

Regional Availability

South and Central America