

Profax™ SL559M

PP

Indelpro S.A. de C.V.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	11	g/10min	ASTM D 1238

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	28	MPa	ASTM D 638
Elongation at Yield	13.2	%	ASTM D 638
Flexural Modulus	1159	MPa	ASTM D 790
Izod Impact notched, 1/8 in	56	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	84	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Blow Molding

Special Characteristics

Anti-static, High impact or impact modified, Transparent

Features

Random Copolymer

Certifications

Food contact, Food approval FDA 21 CFR

Regional Availability

South and Central America