

Profax™ SL872NW

PP

Indelpro S.A. de C.V.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	55	g/10min	ASTM D 1238

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	25.5	MPa	ASTM D 638
Elongation at Yield	5	%	ASTM D 638
Flexural Modulus	1310	MPa	ASTM D 790
Izod Impact notched, 1/8 in	66.6	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	110	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics**Special Characteristics**

Anti-static, High impact or impact modified

Features

High Crystallinity, Nucleated, Impact Copolymer

Certifications

Food contact, Food approval FDA 21 CFR

Applications

Packaging

Regional Availability

South and Central America