

**Purell EP374M**

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	7.5	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	1050	MPa	ISO 527
Yield stress	21	MPa	ISO 527
Yield strain	6	%	ISO 527
Strain at break	>50	%	ISO 527
Charpy notched impact strength, +23°C	45	kJ/m <sup>2</sup>	ISO 179/1eA
Ball indentation hardness	46	MPa	ISO 2039-1

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 0.45 MPa	80	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Density	900	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Injection Molding

**Special Characteristics**

High impact or impact modified

**Features**

Nucleated, Copolymer, Impact Copolymer

**Applications**

Medical

**Regional Availability**

Europe, Asia Pacific, Near East/Africa