

Product Texts

Processing Method: Continuous Filament/Spinning; Fibers; Melt Blown.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	1200	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Characteristics

Processing

Other Extrusion

Features

Barrier Properties, Homopolymer

Delivery form

Pellets

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa