

RANPELEN SFC-750

PP

Lotte Chemical Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	7	g/10min	ISO 1133
Mechanical properties			
ISO Data			
Yield stress	21	MPa	ISO 527
Strain at break	500	%	ISO 527
Flexural modulus, 23°C	735	MPa	ISO 178
Rockwell hardness	R 80	-	ISO 2039-2
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	132	°C	ISO 11357-1/-3
Temp. of deflection under load, 0.45 MPa	70	°C	ISO 75-1/-2
Optical properties			
ASTM Data			
Haze	2	%	ASTM D 1003
Other properties			
Density	900	kg/m ³	ISO 1183

Characteristics**Processing**

Film Extrusion

Additives

Antiblocking agent

Special Characteristics

Transparent

Features

Heat Sealable, High Gloss, Copolymer, Random Copolymer

Certifications

Food contact

Applications

Packaging

Regional Availability

North America, Europe, Asia Pacific