

**RANPELEN SFC-750M**

PP

Lotte Chemical Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	7	g/10min	ISO 1133
<b>ASTM Data</b>			
Melt Flow Index, MFI	7	g/10min	ASTM D 1238
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Yield stress	22	MPa	ISO 527
Strain at break	500	%	ISO 527
Flexural modulus, 23°C	735	MPa	ISO 178
Rockwell hardness	R 77	-	ISO 2039-2
<b>ASTM Data</b>			
Tensile Strength at Yield	22	MPa	ASTM D 638
Elongation at Break	500	%	ASTM D 638
Flexural Modulus	735	MPa	ASTM D 790
Rockwell Hardness	R 77	-	ASTM D 785
Izod Impact notched, 1/8 in	68	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	132	°C	ISO 11357-1/-3
Temp. of deflection under load, 0.45 MPa	72	°C	ISO 75-1/-2
<b>ASTM Data</b>			
DTUL @ 66 psi	72	°C	ASTM D 648
Melting Temperature	132	°C	ASTM D 3418
<b>Optical properties</b>			
<b>ASTM Data</b>			
Haze	2	%	ASTM D 1003
<b>Other properties</b>			
Density	900	kg/m <sup>3</sup>	ISO 1183
Density	900	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Film Extrusion

**Additives**

Antiblocking agent

**Special Characteristics**

Transparent

**Features**

Heat Sealable, High Gloss, Copolymer, Random Copolymer

**Certifications**

Food contact

**Applications**

Packaging

**Regional Availability**

North America, Europe, Asia Pacific