

RE216CF

PP

Borealis A/S

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	11	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Flexural modulus, 23°C	800	MPa	ISO 178

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	145	°C	ISO 11357-1/-3

Optical properties	Value	Unit	Test Standard
ASTM Data			
Gloss	120	-	ASTM D 2457
Haze	2	%	ASTM D 1003

Film Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus, parallel	450	MPa	ISO 527-3
Tensile Modulus, normal	450	MPa	ISO 527-3
Maximum strain, parallel	600	%	ISO 527-3
Maximum strain, normal	600	%	ISO 527-3
Dynamic coefficient of friction	0.5	-	ISO 8295
Thickness of specimen	0.05	mm	-

Characteristics**Additives**

Antiblocking agent

Features

Copolymer, Random Copolymer

Certifications

Food contact

Applications

Packaging

Regional Availability

Europe