

Product Texts

Polypropylene-homopolymer containing 70 % of post-consumer recycled material, natural colour.

Processing/Physical Characteristics

	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	2.5	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties

	Value	Unit	Test Standard
ISO Data			
Yield stress	35	MPa	ISO 527
Yield strain	10	%	ISO 527
Flexural modulus, 23°C	1500	MPa	ISO 178
Izod notched impact strength, +23°C	4.3	kJ/m ²	ISO 180/1A

Characteristics**Processing**

Sheet Extrusion, Blow Molding

Delivery form

Natural Color

Features

Homopolymer

Certifications

Recycled Resin Content

Applications

General Purpose

Regional Availability

Europe