

**Product Texts**

This grade contains 60 % of post-consumer recycled material, natural colour.

**Processing/Physical Characteristics**

	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	4	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

**Mechanical properties**

	Value	Unit	Test Standard
<b>ISO Data</b>			
Yield stress	36	MPa	ISO 527
Yield strain	10	%	ISO 527
Flexural modulus, 23°C	1550	MPa	ISO 178
Izod notched impact strength, +23°C	4	kJ/m <sup>2</sup>	ISO 180/1A

**Characteristics****Processing**

Film Extrusion, Sheet Extrusion, Other Extrusion

**Delivery form**

Natural Color

**Features**

Homopolymer

**Certifications**

Recycled Resin Content

**Applications**

General Purpose, Packaging

**Regional Availability**

Europe