

RESLEN PPC12 V0HF NT 1A0000

PP

Polimarky Spółka Jawna

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	12	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1500	MPa	ISO 527
Strain at break	70	%	ISO 527
Charpy impact strength, +23°C	38	kJ/m ²	ISO 179/1eU

Thermal properties	Value	Unit	Test Standard
ISO Data			
Burning behav. at thickness h	V-0	class	IEC 60695-11-10

Other properties	Value	Unit	Test Standard
Density	1030	kg/m ³	ISO 1183

Characteristics**Delivery form**

Natural Color

Chemical Resistance

Oxidation Resistance

Special Characteristics

Flame retardant, Halogen-free

Regional Availability

Europe