

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	4.2	g/10min	ISO 1133
Temperature	170	°C	-
Load	21.6	kg	-
<b>Other properties</b>			
Density	1540	kg/m <sup>3</sup>	ISO 1183

## Characteristics

### Processing

Wire/Cable Extrusion

### Features

Low Emission, Low Smoke

### Delivery form

Black

### Applications

Electrical and Electronical

### Special Characteristics

Flame retardant, Halogen-free, U.V. stabilized or stable to weather

### Regional Availability

Europe