

**RF366MO**

PP

Borealis A/S

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	20	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	1200	MPa	ISO 527
Yield stress	29	MPa	ISO 527
Yield strain	11	%	ISO 527
Flexural modulus, 23°C	1150	MPa	ISO 178
Charpy notched impact strength, +23°C	5.5	kJ/m <sup>2</sup>	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 0.45 MPa	75	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Density	905	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	200 - 260	°C	-
Mold temperature	30 - 40	°C	-
Holding pressure	20 - 50	MPa	-

**Characteristics****Processing**

Injection Molding, Blow Molding

**Special Characteristics**

Anti-static, Transparent

**Features**

High Gloss, Nucleated, Copolymer, Random Copolymer

**Certifications**

Food contact

**Applications**

Packaging

**Regional Availability**

Europe