

**RI83C**

PP

Hanwha TotalEnergies Petrochemical co. Ltd.

| <b>Processing/Physical Characteristics</b> | <b>Value</b> | <b>Unit</b>       | <b>Test Standard</b> |
|--|--------------|-------------------|----------------------|
| <b>ASTM Data</b>                           |              |                   |                      |
| Melt Flow Index, MFI                       | 25           | g/10min           | ASTM D 1238          |
| <b>Mechanical properties</b>               |              |                   |                      |
| <b>ASTM Data</b>                           |              |                   |                      |
| Tensile Strength at Yield                  | 17.7         | MPa               | ASTM D 638           |
| Elongation at Break                        | 200          | %                 | ASTM D 638           |
| <b>Other properties</b>                    |              |                   |                      |
| Density                                    | 970          | kg/m <sup>3</sup> | ASTM D 792           |

**Characteristics****Processing**

Coating

**Applications**

Automotive

**Special Characteristics**

U.V. stabilized or stable to weather

**Regional Availability**

Asia Pacific