

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	9.3	cm <sup>3</sup> /10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Melt flow index, MFI	7.5	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
<b>Other properties</b>			
Density	905	kg/m <sup>3</sup>	ISO 1183
Bulk density	560	kg/m <sup>3</sup>	-

### Characteristics

#### Delivery form

Pellets, Natural Color

#### Regional Availability

Europe

#### Certifications

Recycled Resin Content