

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	31	cm ³ /10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Melt flow index, MFI	25	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Other properties			
Density	940	kg/m ³	ISO 1183
Bulk density	570	kg/m ³	-

Characteristics

Delivery form

Pellets, Natural Color

Regional Availability

Europe

Certifications

Recycled Resin Content