

**RTP 152 HI HF**

PP

RTP Company

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>20</b>	g/10min	ASTM D 1238
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-
Mold Shrinkage, MD	<b>0.0175</b>	mm/mm	ASTM D 955

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Modulus	<b>827.4</b>	MPa	ASTM D 638
Tensile Strength	<b>13.8</b>	MPa	ASTM D 638
Flexural Modulus	<b>620.5</b>	MPa	ASTM D 790
Flexural Strength	<b>17.9</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>641</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
UL 94 Flame rating	<b>V-2</b>	-	UL 94
Thickness tested	<b>0.794</b>	mm	-
DTUL @ 264 psi	<b>40.6</b>	°C	ASTM D 648

<b>Electrical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Volume Resistivity	<b>&gt;1E15</b>	Ohm*cm	ASTM D 257

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Water Absorption, 24hr	<b>0.01</b>	%	ASTM D 570
Density	<b>930</b>	kg/m <sup>3</sup>	ASTM D 792

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>79.4</b>	°C	-
Pre-drying - Time	<b>2</b>	h	-
Melt temperature	<b>191 - 232</b>	°C	-
Mold temperature	<b>32.2 - 65.6</b>	°C	-
Injection pressure	<b>68.9 - 103</b>	MPa	-

**Characteristics****Processing**

Injection Molding

**Features**

Copolymer

**Special Characteristics**

Flame retardant, High impact or impact modified

**Regional Availability**

North America, Europe, Asia Pacific