

Product Texts

TPO

Processing/Physical Characteristics**Value****Unit****Test Standard****ISO Data**

Melt flow index, MFI

2.5

g/10min

ISO 1133

Temperature

230

°C

-

Load

2.16

kg

-

Mechanical properties**Value****Unit****Test Standard****ISO Data**

Yield stress

23

MPa

ISO 527

Flexural modulus, 23°C

1100

MPa

ISO 178

Izod notched impact strength, +23°C

65kJ/m²

ISO 180/1A

Characteristics**Processing**

Injection Molding, Sheet Extrusion, Other Extrusion

Applications

Automotive

Features

Nucleated, Copolymer, Impact Copolymer

Regional Availability

Europe