

Product Texts

This grade contains 70 % of post-consumer recycled material, natural colour.

Processing/Physical Characteristics

	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	13	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties

	Value	Unit	Test Standard
ISO Data			
Flexural modulus, 23°C	1550	MPa	ISO 178
Izod notched impact strength, +23°C	3	kJ/m ²	ISO 180/1A

Characteristics**Processing**

Injection Molding

Delivery form

Natural Color

Features

Homopolymer

Certifications

Recycled Resin Content

Applications

General Purpose, Packaging

Regional Availability

Europe