

**Product Texts**

Polypropylene resin containing 65% weight of post-consumer recycle.

**Processing/Physical Characteristics**

	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	15	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

**Mechanical properties**

	Value	Unit	Test Standard
<b>ISO Data</b>			
Flexural modulus, 23°C	1400	MPa	ISO 178
Izod notched impact strength, +23°C	6	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	3.5	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	0	°C	-

**Characteristics****Processing**

Injection Molding

**Delivery form**

Pellets

**Special Characteristics**

High impact or impact modified

**Features**

Copolymer, Impact Copolymer

**Certifications**

Recycled Resin Content

**Regional Availability**

Europe