

**Repol AS030N**

PP

Reliance Polymers

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>3</b>	g/10min	ASTM D 1238
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>35</b>	MPa	ASTM D 638
Elongation at Yield	<b>12</b>	%	ASTM D 638
Izod Impact notched, 1/8 in	<b>44</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
DTUL @ 66 psi	<b>105</b>	°C	ASTM D 648

**Characteristics****Features**

Homopolymer

**Certifications**

Food contact, Food approval FDA 21 CFR

**Applications**

Monofilament, Packaging

**Regional Availability**

Europe, Asia Pacific, Near East/Africa