

Repol AS4000N

PP

Reliance Polymers

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	400	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Thermal properties			
ASTM Data			
Melting Temperature	163	°C	ASTM D 3418
Other properties			
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Blown Film Extrusion, Film Extrusion

Delivery form

Pellets

Features

Barrier Properties, Homopolymer

Certifications

Food contact, Food approval FDA 21 CFR

Applications

Medical

Regional Availability

Europe, Asia Pacific, Near East/Africa