

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	90	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Flexural modulus, 23°C	1350	MPa	ISO 178
Izod notched impact strength, +23°C	5.8	kJ/m ²	ISO 180/1A
Izod notched impact strength	4.2	kJ/m ²	ISO 180/1A
Temperature	-20	°C	-
Thermal properties			
ISO Data			
Temp. of deflection under load, 0.45 MPa	104	°C	ISO 75-1/-2

Characteristics

Processing

Injection Molding

Special Characteristics

Anti-static, High impact or impact modified

Features

Low Warpage, Nucleated, Copolymer

Regional Availability

Europe