

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	6	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Yield stress	30	MPa	ISO 527
Flexural modulus, 23°C	1500	MPa	ISO 178
Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 0.45 MPa	110	°C	ISO 75-1/-2

Characteristics

Processing

Injection Molding, Compression Molding

Additives

Antiblocking agent, Release agent

Special Characteristics

High impact or impact modified

Features

Blush Resistance/Low Crease Whitening, Copolymer, Impact Copolymer

Certifications

Food contact

Applications

Packaging

Regional Availability

Europe