

S700

PP

SINOPEC Shanghai Gaoqiao Company

Processing/Physical Characteristics	Value	Unit	Test Standard
Other Standards^[5]			
Melt flow index, MFI	14	g/10min	

S: These properties are reported by the producer according standards that are different to our defaults.

Mechanical properties	Value	Unit	Test Standard
Other Standards^[5]			
Yield stress	31	MPa	
Flexural modulus, 23°C	1200	MPa	

S: These properties are reported by the producer according standards that are different to our defaults.

Characteristics**Regional Availability**

Asia Pacific