

**SABIC® PP 514M12**

PP

Saudi Basic Industries Corporation (SABIC)

| <b>Thermal properties</b> | <b>Value</b> | <b>Unit</b> | <b>Test Standard</b> |
|---------------------------|--------------|-------------|----------------------|
| <b>ASTM Data</b>          |              |             |                      |
| Melting Temperature       | <b>158</b>   | °C          | ASTM D 3418          |

| <b>Other properties</b> | <b>Value</b> | <b>Unit</b>       | <b>Test Standard</b> |
|-------------------------|--------------|-------------------|----------------------|
| Density                 | <b>905</b>   | kg/m <sup>3</sup> | ASTM D 792           |

**Characteristics****Features**

Homopolymer

**Applications**

Packaging