

SABIC® PP 522K

PP

Saudi Basic Industries Corporation (SABIC)

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	3	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	45	MPa	ASTM D 638
Rockwell Hardness	R110	-	ASTM D 785
Izod Impact notched, 1/8 in	40	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	122	°C	ASTM D 648
Vicat Temperature	150	°C	ASTM D 1525
Other properties			
Density	905	kg/m ³	ASTM D 792

Characteristics**Processing**

Thermoforming