

**Product Texts**

SABIC® PP 595A has been specially developed for use in automotive compounding. The material has high flow properties and a high stiffness, enabling high production rates. It is formulated with a dedicated automotive additive package.

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Yield strain	<b>11</b>	%	ISO 527
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>35</b>	MPa	ASTM D 638
Rockwell Hardness	<b>R104</b>	-	ASTM D 785
<b>Thermal properties</b>			
<b>ASTM Data</b>			
DTUL @ 66 psi	<b>108</b>	°C	ASTM D 648