

SABIC® PPcompound 2605

PP

Saudi Basic Industries Corporation (SABIC)

Product Texts

SABIC® PPcompound 2605 is a mineral filled modified polypropylene. Typical material properties include an excellent impact stiffness balance with a low density. Typical applications include automotive interior parts such as trims and dashboards. SABIC® PPcompound 2605 is a designated automotive grade. IMDS ID: 16485887

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	25	g/10min	ISO 1133
Temperature	230	°C	-
Load	5	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1300	MPa	ISO 527
Yield stress	21	MPa	ISO 527
Stress at break	20	MPa	ISO 527
Strain at break	>50	%	ISO 527
Flexural modulus, 23°C	1400	MPa	ISO 178
Charpy notched impact strength, +23°C	N	kJ/m ²	ISO 179/1eA
Izod notched impact strength	5.5	kJ/m ²	ISO 180/1A
Shore D hardness	60	-	ISO 7619-1

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 0.45 MPa	90	°C	ISO 75-1/-2
Vicat softening temperature, A	140	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density	960	kg/m ³	ISO 1183