

Product Texts

SABIC® PPcompound 5310 is a mineral filled, impact modified polypropylene TPO. This material combines scratch resistance and heat stability with exterior automotive weathering stability. IMDS ID: 209727767

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	19	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1310	MPa	ISO 527
Yield stress	21	MPa	ISO 527
Yield strain	5.4	%	ISO 527
Stress at break	14	MPa	ISO 527
Strain at break	>50	%	ISO 527
Flexural modulus, 23°C	1310	MPa	ISO 178
Charpy notched impact strength, +23°C	17	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	3	kJ/m ²	ISO 179/1eA
Izod notched impact strength	3	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	55	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	92	°C	ISO 75-1/-2
Vicat softening temperature, A	133	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density	960	kg/m ³	ISO 1183
Density	960	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 100	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	210 - 270	°C	-
Mold temperature	15 - 60	°C	-
Zone 1	190 - 230	°C	-
Zone 2	200 - 250	°C	-
Zone 3	210 - 270	°C	-
Nozzle temperature	210 - 270	°C	-
Back pressure	1 - 1.5	MPa	-

Characteristics**Special Characteristics**

High impact or impact modified, Heat stabilized or stable to heat