

Product Texts

SABIC® PPcompound 7995 is a mineral filled modified polypropylene. This material combines a very high flow with a good scratch resistance and a good stiffness. This material has a very broad processing window and good esthetical performance. Typical applications include esthetical automotive interior parts such as door panels and interior trim. SABIC® PPcompound 7995 is a designated automotive grade. IMDS ID: 16487332

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	30	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2000	MPa	ISO 527
Yield stress	25	MPa	ISO 527
Stress at break	21	MPa	ISO 527
Strain at break	50	%	ISO 527
Flexural modulus, 23°C	2100	MPa	ISO 178
Charpy notched impact strength, +23°C	8	kJ/m ²	ISO 179/1eA
Izod notched impact strength	2.5	kJ/m ²	ISO 180/1A
Shore D hardness	66	-	ISO 7619-1

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 0.45 MPa	105	°C	ISO 75-1/-2
Vicat softening temperature, A	130	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density	1040	kg/m ³	ISO 1183