

Product Texts

PE < 5 %

Processing/Physical Characteristics

	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	25	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties

	Value	Unit	Test Standard
ISO Data			
Flexural modulus, 23°C	1150	MPa	ISO 178
Izod notched impact strength, +23°C	4.5	kJ/m ²	ISO 180/1A

Thermal properties

	Value	Unit	Test Standard
ISO Data			
Vicat softening temperature, B	73	°C	ISO 306

Other properties

	Value	Unit	Test Standard
Density	920	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Certifications

Recycled Resin Content

Delivery form

Pellets

Regional Availability

North America, Europe, Asia Pacific, South and Central America